

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
4 April 2002 (04.04.2002)

PCT

(10) International Publication Number  
**WO 02/27137 A1**

(51) International Patent Classification<sup>7</sup>: **E21B 33/12, 36/00, 33/13**

(21) International Application Number: **PCT/GB01/04260**

(22) International Filing Date:  
24 September 2001 (24.09.2001)

(25) Filing Language: **English**

(26) Publication Language: **English**

(30) Priority Data:  
0023543.2 26 September 2000 (26.09.2000) **GB**

(71) Applicant (for US only): **RAWWATER ENGINEERING COMPANY LIMITED** [GB/GB]; Rawwater House, 102 Hob Hey Lane, Culceth, Cheshire WA3 4NW (GB).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **EDEN, Robert, David** [GB/GB]; 102 Hob Hey Lane, Culceth, Cheshire WA3 4NW (GB). **EDEN, Robert, Henry** [GB/GB]; 102 Hob Hey Lane, Culceth, Cheshire WA3 4NW (GB).

(74) Agent: **ALLMAN, Peter, John**; Marks & Clerk, Sussex House, 83-85 Mosley Street, Manchester M2 3LG (GB).

(81) Designated States (national): **AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.**

(84) Designated States (regional): **ARIPO** patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), **Eurasian** patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), **European** patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), **OAPI** patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

**Published:**

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: **WELL SEALING METHOD AND APPARATUS**

(57) Abstract: A method for forming a plug in a well comprises filling a length of the well with a molten material the melting point of which is higher than the temperature within the well and which expands as it solidifies upon cooling to the temperature within the well. Also an apparatus for forming a plug in a well comprises means for filling a length of the well with a molten material the melting point of which is higher than the temperature within the well and which expands as the material solidifies upon cooling to the temperature within the well.

Best Available Copy

WO 02/27137 A1

## WELL SEALING METHOD AND APPARATUS

The present invention relates to a method and apparatus for sealing underground components to prevent leakage of for example hydrocarbon fluids from those components.

In the oil and gas extraction industries, abandoned wells have to be plugged to keep the contents of deep high pressure environments which communicate with those wells from invading levels at or adjacent the surface. Plugs can be inserted at any point in a well, for example adjacent the surface or at a substantial depth. Typically, plugs are formed by injecting cement or resin into the well so as to fill for example a fifty metre length of the well. Experience has proved however that such plugs are not particularly reliable and often leak.

The known plugs tend to leak for a variety of reasons. Firstly, as the well wall is typically not particularly clean and is also covered with a hydrocarbon film, it is difficult to produce a reliable contiguous seal. Often a contiguous seal of only a metre or so in length is formed with a plug fifty times that length. Furthermore, as cement and resin based plugs solidify they contract which tends to open up a gap between the plug and the well wall. Although when a plug is initially inserted there may be little dynamic pressure in the well, after the plug is in situ substantial pressures can build up and as a result a plug which appears initially to be working satisfactory may subsequently be found to leak. If hydrocarbons leak past the plug contamination of the surface environment or for example a sub-surface aquifer can result. It is well known in the industry that a significant proportion of abandoned wells leak. As a result leaking abandoned wells often have to be re-plugged which is an expensive and time consuming operation.

It is known to form temporary seals in chemical plants by freezing water or other fluids in the plant. Such plugs are used for example to seal pipes whilst work is conducted upon systems connected to those pipes. The advantage of this approach is that the system does not need to be drained prior to work being initiated. Ice plugs do form reliable seals but require continuous cooling given that the sealed pipe will normally be at a temperature above melting point of ice.

It is an object of the present invention to provide a method and apparatus for plugging a well which obviates or mitigates the problems outlined above.

According to the present invention, there is provided a method for forming a plug in a well, wherein a length of the well is filled with a molten material the melting point of which is higher than the temperature within the well and which expands as it solidifies.

The material may be a metal alloy, for example a low-melting point bismuth-containing alloy such as "Rose's metal", "Kraft's alloy" or "Homberg's alloy". The bismuth-containing alloy may be doped with sodium. Such alloys expand upon solidification and thus once deposited in a well they lose heat into the surrounding environment, solidify, and in solidifying expand to form a secure plug within the well.

The material may be delivered to the well in a molten state. For example a canister of molten material may be lowered to the intended site of the plug and opened either by remote control or deliberate rupture of the canister. For sodium doped material the doping may be achieved by adding an ingot of sodium to the material when in a molten state when the alloy is first prepared. The sodium is added when the alloy is first manufactured, not "down-hole" when it is used to form the plug.

Alternatively, the material may be delivered to the well in a solidified state, subsequently melted in the well, and then allowed to solidify. For example, the material could be delivered in granular form, for example in a carrier fluid. The granular material could then be melted in any suitable manner, thereafter cooling to form a solidified plug. The granular material could be melted by delivering it in a first fluid, then adding a second fluid which when mixed with the first elevates the temperature to above the melting point of the granular material. The granular material then melts, and subsequently cools to form a solidified plug. The first fluid could be for example inhibited hydrochloric acid whereas the second could be for example caustic soda.

As a further alternative the plug material may be delivered to the well and located therewithin mounted in solid form on a carrier. Such a carrier may comprise a chemical heater, for example a "Thermit" mixture, which when ignited provides thermal energy to melt the plug material when it is located at the required well depth.

The carrier may incorporate an engagement means to engage the well casing when in position. Such engagement means may be arranged to allow insertion of the carrier into the well and movement in a down-hole direction therein but prevent up-hole movement. This may be achieved by coupling the engagement means to the carrier via a hinge.

Non-chemical methods of melting the plug material could of course be used, for example steam, heated water, electrical resistance heating, frictional heating, sonothermic (sound generated) heating, cavitation (pressure generated) heating, or even simply introducing a solid high thermal capacity mass from which heat is transferred into the previously deposited granular material.

As a further alternative, a first component of the material which has a melting point lower than the temperature within the well may be delivered in a molten state, and a second component may then be added to the first, the second component mixing with the first and the resultant mixture having a melting point which is higher than the temperature within the well. Thus the first component could be accurately positioned in situ, visually inspected and then converted into a solid plug simply by pouring the second component into the well so that it mixes with the first component.

Once the molten material has solidified and formed a plug it may be capped with a coating material. A preferred example of a suitable coating material is concrete.

Embodiments of the present invention will now be described, by way of example, with reference to the accompanying drawings in which;

Figure 1 is a schematic representation of a conventional well plugging method;

Figure 2 is a schematic representation of a first method for plugging a well in accordance with the present invention;

Figure 3 is a schematic representation of a second method for plugging a well in accordance with the present invention;

Figure 4 is a schematic representation of a third method for plugging a well in accordance with the present invention;

Figures 5, 6 and 7 are side views of components used in the third method;

Figures 8, 9 and 10 are schematic cross-sections (viewed from the side) of components used in the third method;

Figure 11 is a schematic representation of a fourth method for plugging a well in accordance with the present invention; and

Figures 12 and 13 are side views of components used in the fourth method.

Referring to figure 1, an oil well has a casing 1 within which production tubing 2 extends axially. In order to plug the well, it is necessary to block both the annular passageway between the casing 1 and the production tubing 2 itself. Conventionally this is achieved by blocking the casing 1 beneath the production tubing 2 by inserting a packer 3. The space above the packer 3 is then filled with cement 4 to a depth typically of 50 metres. The cement then solidifies, forming the required plug.

The surface of the casing 1 and the surface of the production tubing 2 contacted by the cement are not ideal for forming sealing interfaces. Those surfaces are contaminated with hydrocarbon components and other deposits. Furthermore, as the cement hardens, it tends to contract so that in the absence of adhesion between the cement 4 and the casing 1 an annular gap can develop between the cement 4 and the casing 1. Although at the time the well is plugged generally there will be little upwards flow through the well because the seal is initially adequate, over time the seal can fail so that fluids will migrate up the gap created by seal failure. As a result unwanted fluid can leak past the plug 4 (shown by arrow 5), risking contamination of the local environment.

Referring now to figure 2, this illustrates a first embodiment of the present invention. The same reference numerals are used for equivalent components as in figure 1. In contrast to the cement plug 4 of figure 1 however in figure 2 a bismuth alloy plug 6 is formed within the casing 1 above the packer 3. The length of casing 1 filled with the plug 6 is relatively small as compared with the length of casing filled by the cement 4 as shown in figure 1. Typically the length of casing 1 filled with the plug 6 is an order magnitude less than that often encountered with cement plugs (typically 50 metres). Nevertheless, the arrangement of figure 2 provides a reliable plug 6 because the bismuth alloy is initially molten within the casing 1 but subsequently solidifies and during solidification expands to tightly engage the casing

1 and the production tubing 2. Thus a solid plug 6 of expanded metal seals the casing 1 and locks together and components contracted by the plug 6.

The bismuth alloy plug 6 could be formed from one of the low-melting point bismuth containing alloys known from the printing industry, for example "Rose's metal" (melting point 93°C), "Kraft's alloy" (melting point 104°C), "Homborg's alloy" (melting point 122°C) or any alloy which may be developed to have characteristics suitable for the down-hole conditions. For example antimony could be used to form higher temperature melting point alloys. Such alloys increase in volume upon solidification and thus are sometimes referred to as "expanding metal alloys". The unusual property of expansion upon solidification has been used to advantage in the printing industry to lock printing blocks into printing frames. In the environment to which the present invention relates, once installed the bismuth alloy plug 6 will be a permanent fixture given that the stable temperature of the local environment ensure that it remains in a solid state. As the plugs expand on solidification, they form reliable seals along their entire length.

The solid plug 6 of figure 2 can be formed by delivering molten bismuth alloy in a canister or the like which is lowered to just above the packer 3 and then opened or ruptured as convenient. The released molten alloy flows to form a solid plug 6 above the packer 3 and then cools to the local temperature (typically 40-100°C). Thus the plug 6 solidifies and expands. Alternatively, the alloy could be delivered via a coiled tubing placement system.

Optionally the bismuth alloy may be doped with sodium. This may be achieved by adding an ingot of sodium to the bismuth alloy when it is molten during the manufacturing process. It will be appreciated that as sodium melts at a low temperature (98°C) it will melt in the molten alloy and become dispersed. Other methods of doping such as ion bombardment and pre-doping of the bismuth alloy before it is located in situ are not hereby precluded. The doping of the bismuth alloy may be such that around 1% of the alloy is comprised of sodium. It is postulated that doping with sodium serves as an aid in preventing creep of the bismuth alloy plug 6.

As an alternative to delivering molten alloy to the space above the packer 3, it would be possible to deliver a solid alloy in for example granular form and then to

melt the alloy in situ using any convenient heating system. Figure 3 illustrates one arrangement in which the necessary heating is delivered by an exothermic reaction.

Referring to figure 3, this illustrates a second embodiment of the present invention. Once again the same reference numerals are used as in figure 1 where appropriate. The space above the packer 3 however is filled with a layer of bismuth alloy granules 7 immersed in a carrier fluid of for example inhibited hydrochloric acid 8. The acid 8 cleans the surfaces of the down hole components above the packer 3 but does not attack the metal of the down hole components nor the bismuth alloy granules 7. All of the introduced materials will warm up to the local ambient temperature. This is too low to cause the granules to melt. A further component can then be added, that is caustic soda (illustrated by arrow 9), which reacts with the hydrochloric acid 8 in an exothermic reaction that elevates the local temperature to above the melting point of the alloy granules 7. The granules 7 thus melt and coalesce. In most applications, the local pressure will be sufficiently high to prevent the reactants from boiling and dissipating the generated heat. The end reaction products of the cooled acid 8/alkali 9 reaction are sodium chloride and water which are benign to the natural environment. It will of course be appreciated that other exothermic reactions could be used. It will also be appreciated that any other convenient method for melting the alloy granules 7 could be used.

Referring now to figures 4-10 a third embodiment of the invention is illustrated using the same reference numbers as above where appropriate. Once again a bismuth alloy plug 6 is formed within the casing 1 above the packer 3. In contrast to the first and second embodiments of the invention, the solid bismuth alloy plug 6 (shown in figure 4) is formed from an amount of bismuth alloy delivered in solid form on a carrier spool to the required depth within the casing 1.

The carrier spool may comprise 1% manganese steel. The carrier spool comprises a tubular mandrel 10. The mandrel 10 has an upper open end. The lower end of the mandrel 10 terminates in a head 11, upon which a cylindrical packer 3 (preferably comprising vulcanised rubber including 40% acrylonitrile) is mounted. The packer 3 may be mounted on the head by a method which includes a bonding step, thus forming a metallelastic bond. The head 11 defines a frustocone the base of which has a lower diameter than that of the packer 3 and which tapers from the upper

surface of the packer 3 to the mandrel 10. The mandrel 10 has a plurality of circular flanges 12 in the form of fins distributed at intervals along its length. The diameter of each fin 12 is approximately equal to the diameter of the base of the frustocone 11.

In delivery form (shown in figure 6) the solid metal locates along the length of the mandrel 10 between the head 11 and an upper fin 12, defining a cylinder extending as far as the peripheral edge of the upper fin 12. The metal may comprise, for example, pure bismuth, an admixture of 95% bismuth and 5% tin or an admixture of 52% bismuth and 48% tin, in each case the metal may be doped with sodium. In this form the carrier spool is inserted into the casing 1 (packer end first) and lowered to the required depth.

Thus positioned the bismuth alloy is melted in situ by a heater which normally locates within the mandrel 10 (but which is illustrated for clarity in figure 7 outside the mandrel 10). The heater defines a cylinder, an upper portion of which comprises an ignition source 13 and a lower portion of which comprises a heater element 14. The heater element 14 may comprise an admixture of aluminium and iron oxide (thermit mixture). The ignition source 13 may comprise a barium peroxide fuse and an electrical heater. It will be appreciated that other forms of both ignition source 13 and heater element 14 could be used.

Commonly the ignition source 13 is activated using a fuse 15. The fuse 15 is preferably disposed in a bore 16 in a threaded cap 17 which engages a threaded portion 18 of the mandrel 10. The cap 17 may define a simple hollow plug (as shown in figure 8) or may include features such as incisions 19 (as shown in figure 9) which allow the cap 17 to be engaged by other equipment (not shown) such as a deployment tool. The cap 17 may define a stab connector.

Activation of the detonator 13 triggers the heater element 14. Heat produced from the heater element 14 causes the bismuth alloy supported on the mandrel 10 to become molten. Combustion/waste gases which may be produced from the heater element 14 are allowed to be vented by the open end of the mandrel 10 and the cap 17.

The molten bismuth alloy thus slumps into the volume defined by the upper surface of the rubber packer 3 and the casing wall 1 (as shown in figure 6).



The frustocone 11 is able to serve as a wedge that drives into the expanded bismuth alloy plug 6. Thus pressure from the reservoir serves to force the plug 6 against the casing wall 1.

The fins 12 serve three purposes. Firstly the fins 12 aid in forcing the expanding metal against the casing 1 by minimising axial and promoting lateral expansion. Secondly the fins 12 aid the transfer of heat from the heater element 14 to the bismuth alloy. Thirdly the fins 12 aid in reducing creep of the bismuth alloy plug 6 up hole.

Referring now to figures 11 to 13 a fourth embodiment of the invention is illustrated. Once more a bismuth alloy plug 6 is formed within the casing 1 above a packer 3. The bismuth alloy is delivered using a carrier spool as in the third embodiment. The fourth embodiment differs from the third embodiment in that casing engagement means are coupled to a fin 12 on the carrier spool.

The casing engagement means comprises arms 20a and 20b coupled by a hinge (not shown) to an upper surface of a fin 12. Although two arms 20a, 20b are illustrated coupled to one fin 12 it will be appreciated that additional arms may be included, either coupled to the same or other fins 12. The non-coupled ends of arms 20a and 20b have one or a plurality of casing engagement members (not shown), which may comprise for example a spike, a tooth, a chisel or another engagement member.

In delivery form the arms 20a, 20b are retained within the bismuth alloy so that the carrier spool carrying the bismuth alloy may be located at the required depth in the casing 1. Activation of the heater element 14 causes the bismuth alloy to be melted and thus the arms 20a, 20b are free to fall into engagement with a portion of the casing 1.

As the bismuth alloy solidifies and expands the arms 20a, 20b are urged into a pressured engagement with the casing 1. Thus deployed the arms 20a, 20b act as an aid in preventing reservoir pressure induced creep of the plug 6 along the well. Indeed any increase in reservoir pressure will merely cause stronger engagement of the engagement means with the casing 1.

In a further embodiment of the invention which is not specifically illustrated, an alloy could be introduced the melting point of which is lower than the ambient

temperature immediately above the packer 3. The composition of the alloy could then be changed to raise its melting point above the local ambient temperature. For example, alloys are known which have melting points below 40°C but into which lead can be introduced to form a mixture the melting point of which is well above 40°C. Thus one could envisage the formation of a plug by pouring a first component into the well so as to form a body of liquid alloy immediately above a packer, inspecting the deposited liquid alloy to ensure that the alloy is safely retained in place, and then simply pouring lead granules into the well such that the granules become immersed in the liquid alloy, causing the combined liquid/alloy lead granule mixture to form a solid plug.

In a yet further embodiment of the invention which is not specifically illustrated a further plug may be formed above the plug of solidified material. Such a further plug may be used to provide additional resistance against creep of the plug of scheduled material caused by pressure from the reservoir. As the further plug is not being used to provide a seal for the well its length need not be of the same order of magnitude as conventional plugs described in the prior art. For example the further plug may be of the order of 5-10 metres long. A preferred material for the further plug is concrete.

CLAIMS

1. A method for forming a plug in a well, wherein a length of the well is filled with a molten material the melting point of which is higher than the temperature within the well and which expands as it solidifies.
2. A method according to claim 1, wherein the material is a metal alloy.
3. A method according to claim 2, wherein the material is a bismuth-containing alloy.
4. A method according to claim 1, 2 or 3, wherein the material is delivered to the well in a molten state.
5. A method according to claim 1, 2 or 3, wherein the material is delivered to the well in a solidified state, subsequently melted in the well, and then allowed to solidify.
6. A method according to claim 1, 2 or 3, wherein a first component of the material which has a melting point lower than the temperature within the well is delivered to the well in a molten state, and a second component is added to the first, the second component mixing with the first and the resultant mixture having a melting point which is higher than the temperature within the well.
7. A method according to any one of the preceding claims wherein the material is doped with sodium.
8. A method according to any one of the proceeding claims comprising adding a further plug above the material when solidified.
9. A method according to claim 8 wherein the further plug comprises concrete.

10. An apparatus for forming a plug in a well comprising means for filling a length of the well with a molten material the melting point of which is higher than the temperature within the well and which expands as the material solidifies.

11. An apparatus according to claim 10, comprising a carrier for locating material in solid form within the well.

12. An apparatus according to claim 11, comprising a heater element.

13. An apparatus according to claim 11 or 12, comprising arms which in use engage the well to resist creep of the carrier and solidified material up the well.




FIG. 2





FIG 3






Fig 4






Fig 5




Fig 6




Fig 7




Fig 8




Fig 9




Fig 10




Fig 11




Fig 12






Fig 13

## INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 01/04260

A. CLASSIFICATION OF SUBJECT MATTER  
 IPC 7 E21B33/12 E21B36/00 E21B33/13

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 E21B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2 298 129 A (IRONS CARROLL R) 6 October 1942 (1942-10-06) the whole document	1-5, 10
X	US 4 489 784 A (MESSENGER JOSEPH U) 25 December 1984 (1984-12-25)	1-5, 10-12
Y	abstract; claims 6-10	7-9
Y	US 4 275 788 A (SWEATMAN RONALD E) 30 June 1981 (1981-06-30) column 10, line 42	7
Y	US 1 631 419 A (KINLEY MYRON M) 7 June 1927 (1927-06-07) figure 3	8, 9
	-/-	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

## \* Special categories of cited documents:

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- \*&\* document member of the same patent family

Date of the actual completion of the international search

21 January 2002

Date of mailing of the international search report

05/02/2002

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
 NL - 2280 HV Rijswijk  
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
 Fax (+31-70) 340-3016

Authorized officer

Fonseca Fernandez, H

## INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 01/04260

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 3 273 641 A (H.A. BOURNE) 20 September 1966 (1966-09-20) claims	1, 10
A	US 3 738 424 A (OSMUN D ET AL) 12 June 1973 (1973-06-12) the whole document	10-13
A	US 3 420 928 A (BROWN NORMAN F) 7 January 1969 (1969-01-07) the whole document	1, 10
A	US 3 333 635 A (CRAWFORD JOHN M) 1 August 1967 (1967-08-01) column 4, line 14 - line 36; claim 5	1, 10
A	US 3 419 074 A (BROWN NORMAN F) 31 December 1968 (1968-12-31)	
A	US 3 208 530 A (ALLEN THOMAS O ET AL) 28 September 1965 (1965-09-28)	

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 01/04260

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 2298129	A	06-10-1942	NONE	
US 4489784	A	25-12-1984	NONE	
US 4275788	A	30-06-1981	NONE	
US 1631419	A	07-06-1927	NONE	
US 3273641	A	20-09-1966	NONE	
US 3738424	A	12-06-1973	NONE	
US 3420928	A	07-01-1969	NONE	
US 3333635	A	01-08-1967	NONE	
US 3419074	A	31-12-1968	NONE	
US 3208530	A	28-09-1965	NONE	

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☒ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**